

Release K 100 E

Description

RELEASE K 100 E is a release coat for coextrusion on PE and PP films.

Application

RELEASE K 100 E allows achieving a consistent release thickness and obtaining regular release properties over all the film width.

This product does not need solvents. Therefore it is safer than the usual solutions, allowing significant savings avoiding the costs of solvent drying and recovery.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	99±1
5. Melting Range	°C	90 - 96

Handling

RELEASE K 100 E must be added to the polymer and mixed well (by melting and extrusion/granulation) before coextrusion.

Suggested quantity: 2% in PE and 2-4% in PP.

Masterbatch will be coextruded over the film.

Packing

Fiber drums containing 25 kg plastic bags.

Storing

Store in a fresh, dry place. Shelf-life is 2 years.